

### Black Sand Samples: Gold and Silver Recovery

	<u>Location</u> <u>Northing:Easting</u>	<u>Head Grade</u>		<u>Recovery (48 hrs)</u>	
		<u>Au (g/t)</u>	<u>Ag (g/t)</u>	<u>Au (%)</u>	<u>Ag (%)</u>
Black Sand Composite		3.45	45.2	69	61
Sample "A"	331+47N; 802+62E	1.19	29.3	89.8	81.2
Sample "B"	331+43N; 801+06E	7.41	84.0	80.5	53.0
Sample "C"	331+43N; 800+70E	6.93	117	45.6	36.5
Sample "D"	331+45N; 799+09E	1.19	8.3	80.3	82.7